

This listing of the claims replaces any and all prior versions and listings of claims in the application:

LISTING OF THE CLAIMS

1. (Currently amended) A method of improving the solubility of perfluorinated polyethers in fluorinated solvents, comprising combining a perfluorinated polyether with a solubilizer and a fluorinated solvent to form a solution, wherein the solubilizer is selected from the group consisting of tetrahydrofuran, 2-methyl-tetrahydrofuran, tetrahydropyran, and dioxane alcohols and cyclic ethers, and wherein the solution comprises about 0.001-1 parts by weight of perfluorinated polyether to about 99-99.999 parts by weight of the solvent and solubilizer combined, and further wherein the weight ratio of solubilizer to fluorinated solvent is either about the azeotropic ratio or within the range of about 2:98 to 10:90, or is both about the azeotropic ratio and within the range of about 2:98 to 10:90.

2-5. (Canceled).

6. (Original) The method of claim 1, wherein the solution is formed by first adding the solubilizer to the solvent, followed by the addition of the perfluorinated polyether.

7. (Original) The method of claim 1, wherein the solution is formed by first adding the perfluorinated polyether to the solvent, followed by the addition of the solubilizer.

8. (Original) The method of claim 1, wherein the solution is formed by simultaneously adding the solubilizer and the perfluorinated polyether to the solvent.

9. (Currently amended) The method of claim 1, wherein the fluorinated solvent is selected from the group consisting of hydrochlorofluorocarbons, hydrofluoroethers, hydrofluorocarbons, hydrohalofluoroethers, fluorinated amines, and fluorinated cyclic ethers.

10. (Currently amended) A method of dissolving a perfluorinated polyether for use in hard disk drive applications, comprising:

- (a) providing a fluorinated solvent; and
- (b) adding a solubilizer and a perfluorinated polyether to the solvent;

wherein the solubilizer is a cyclic ether selected from the group consisting of tetrahydrofuran, 2-methyl-tetrahydrofuran, tetrahydropyran, and dioxane ~~selected from alcohols and cyclic ethers~~, and wherein the solution comprises about 0.001-1 parts by weight of perfluorinated polyether to about 99-99.999 parts by weight of the solvent and solubilizer combined, and further wherein the weight ratio of solubilizer to fluorinated solvent is either within the range of about 2:98 to 10:90 or is about the azeotropic ratio, or is both about the azeotropic ratio and within the range of about 2:98 to 10:90.

11-14. (Canceled).

15. (Original) The method of claim 10, wherein the solubilizer is first added to the solvent, followed by the addition of the perfluorinated polyether.

16. (Original) The method of claim 10, wherein the perfluorinated polyether is first added to the solvent, followed by the addition of the solubilizer.

17. (Original) The method of claim 10, wherein the solubilizer and the perfluorinated polyether are added simultaneously to the solvent.

18-34. (Canceled).